

# ELASTOSIL<sup>®</sup> AUX STABILIZER H1



## Silicone Rubber Additives

ELASTOSIL<sup>®</sup> AUX STABILIZER H1 is a ready-to-use compound consisting of a heat stabilizing filler and a reactive silicone polymer which is typically contained in ELASTOSIL<sup>®</sup> high-consistency rubber grades. This ensures that the batch is incorporated into the elastomer during vulcanization and thus does not show any migration.

## Properties

- Paste consistency, can be easily incorporated into ELASTOSIL<sup>®</sup> R and R plus mixtures on two-roll mills.
- No impairment of ELASTOSIL<sup>®</sup> R and R plus grades when concentration recommendations are observed.
- Compatible with curing agents ELASTOSIL<sup>®</sup> AUX CURING AGENT C1, C6 and E as well as ELASTOSIL<sup>®</sup> AUX BATCH PT 1 and PT 2.

## Specific features

- Additive
- Food-contact
- Heat resistant

## Technical data

### General Characteristics

Property	Condition	Value	Method
Color	-	red	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Processing

ELASTOSIL® AUX STABILIZER H1 is incorporated into ELASTOSIL® R and R plus high-consistency rubber using common mixing techniques. Good results are obtained by incorporating the curing agent at the same time.

The recommended concentration of ELASTOSIL® AUX STABILIZER H1 is 3%. Increasing the recommended concentration does not further improve the heat resistance of the compound. At high concentrations of ELASTOSIL® AUX STABILIZER H1 a slightly decrease in hardness values may be obtained with compounds of silicone bases with high Shore A hardness values.

For detailed information please refer to the latest edition of our brochure "SOLID AND LIQUID SILICONE RUBBER - MATERIAL AND PROCESSING GUIDELINES".

## Packaging and storage

### Packaging

This product is available in 1 kg cardboard and 5 kg pail packaging.

### Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code ELASTOSIL® AUX STABILIZER H1



**For technical, quality or product safety questions, please contact:**

**Wacker Chemie AG**, Hanns-Seidel-Platz 4, 81737 Munich, Germany  
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.