

ELASTOSIL[®] R 701/40 S



High Consistency Silicone Rubber (HCR)

ELASTOSIL[®] R 701/40 S is a HCR grade for compression molded products.

Properties

- Good heat- and reversion-stabilised
- Excellent resistance to mineral oil
- Non-post-cure properties:

The differences in the mechanical properties of post- cured and non-post-cured vulcanizates are only very slight.

Specific features

- Low compression set
- Oil resistant

Technical data

Properties Cured

Cure conditions: 0.7 % ELASTOSIL® AUX Crosslinker C1 (Dicumylperoxide), 15 min / 165 °C in press, post-cured 4 h / 200 °C

Property	Condition	Curing Agent C1	Method
Appearance	-	opaque	-
Density	23 °C	1.10 g/cm ³	DIN EN ISO 1183-1 A
Hardness Shore A	-	40	ISO 7619-1
Tensile strength	-	6.9 N/mm ²	ISO 37 type 1
Elongation at break	-	460 %	ISO 37 type 1
Compression Set	22 h 175 °C	7 %	DIN ISO 815-1 type B method A
Rebound resilience	-	66 %	ISO 4662
Tear strength	-	15 N/mm	ASTM D 624 B

These figures are only intended as a guide and should not be used in preparing specifications.

Oil resistance

Cure conditions: 0.7 % ELASTOSIL® AUX Crosslinker C1 (Dicumylperoxide), 15 min / 165 °C in press, post-cured 4 h / 200 °C

Property	70 h / 150 °C IRM 901	70 h / 150 °C IRM 903	Method
Hardness Shore A	37	29	ISO 7619-1
Tensile strength	7.7 N/mm ²	3.5 N/mm ²	ISO 37
Elongation at break	480 %	250 %	ISO 37
Volume change	6 %	56 %	-

These figures are only intended as a guide and should not be used in preparing specifications.

Oil resistance

Cure conditions: 0.7 % ELASTOSIL® AUX Crosslinker C1 (Dicumylperoxide), 15 min / 165 °C in press, post-cured 4 h / 200 °C

Property	500 h / 150 °C Lubrizol® OS 206 304	Method
Hardness Shore A	23	ISO 7619-1
Tensile strength	4.6 N/mm ²	ISO 37
Elongation at break	390 %	ISO 37
Volume change	24 %	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Automotive Parts
- Molded Parts
- Aerospace
- Roller Coatings

Application details

The compounds are recommended for all kinds of seals that come into contact with mineral oils.

ELASTOSIL® R 701/40 S is used especially when low compression set is crucial for achieving good seal properties. The compounds may also be used for making high quality silicone-rubber-covered rollers.

Processing

ELASTOSIL® R 701/40 S is not recommended for the extrusion. ELASTOSIL® R 701/40 S can be vulcanized with peroxides normally used for press molding silicone rubber.

For detailed information please refer to the latest edition of our brochure "SOLID AND LIQUID SILICONE RUBBER - MATERIAL AND PROCESSING GUIDELINES".

Packaging and storage

Packaging

This product is available in 20 kg and 540 kg cardboard packaging.

Special delivery forms are possible but depend on several technical and commercial aspects. Please contact your local sales manager in such cases.

Storage

Please store the cardboard boxes in a dry and cool place. Already opened boxes should be closed again to avoid any contamination.

The 'Best use before end' date of each batch is shown on the product label.
Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® R 701/40 S



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.