

WACKER® PRIMER G 719

Primer for silicone rubber

solvent-based mixture of siloxanes and reactive silanes used as adhesion promoter for silicone rubbers

Properties

- Provides excellent adhesion onto various substrates.
- Solvent based
- Various application methods (e.g. coating, dipping, brushing, spraying)
- Further dilution in organic solvents possible

Technical data

General Characteristics

Property	Condition	Value	Method
Appearance	-	yellow to red	-
Density	23 °C	0.9 g/cm ³	ISO 2811
Dissipation factor	50 Hz	5 x 10 ⁻³ tan δ	IEC 62631-2-1
Electric strength	-	25 kV/mm	IEC 60243-1
Solid Content	-	25 %	-
Viscosity	-	3 mm ² /s	DIN 51562-1
Volume resistivity	-	10 ¹⁶ Ohmcm	IEC 62631-3-1

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Application details

WACKER® PRIMER G 719 is a solution of a siloxanes and reactive silanes in organic solvents. It is used to pretreat metallic, ceramic, glass or other polymeric substrate surfaces to enable excellent adhesion towards subsequently vulcanized ELASTOSIL® R plus or LR silicone elastomers (addition curing).

After the solvents have evaporated, a rigid film of silicone resin is formed on exposure to atmospheric humidity. The primer film adheres firmly to a large variety of substrates and serves as adhesion promoter for subsequently applied silicone rubbers.

Processing

It is recommended to clean all substrate surfaces with solvents (e.g. white spirits followed by ethanol or acetone) prior to the application of WACKER® PRIMER G 719. The primer may be applied directly or in diluted form with a variety of application methods (e.g. coating, dipping, brushing or spraying). It is recommended to stir the primer thoroughly before application.

The resulting primer layer should be as thin as possible. Usually the best results can be achieved with a primer layer between 1 and 10 µm thickness. If the primer needs to be diluted, organic solvents like white spirits or ISOPAR® E can be used in a ratio of 1:1 - 1:10.

After application of the primer, the solvent should be evaporated at room temperature and moderate atmospheric humidity for at least 30 minutes to allow for the formation of a consistent primer film. It is recommended to apply the silicone rubber soon afterwards, but not later than 2 days. In some cases the adhesion can be improved by heating the primed substrate after evaporation of the solvents to 100°C for up to one hour.

It is important to note that in some cases the initial adhesion will be sufficient for handling while the maximum adhesive strength will be achieved after a few days.

When adhesion of silicone elastomers onto very smooth substrates has to be achieved it is recommended to roughen the surface by grinding or blast cleaning. In case of metals the substrate should be given several hours time to regenerate its oxygen layer before applying WACKER® PRIMER G 719.

Since adhesion is determined by the nature of the substrate, the applied silicone elastomer and the processing parameters, proper trials are absolutely necessary.

Packaging and storage

Packaging

This product is available in 0.8 kg bottles, 20 kg pails and 160 kg drums.

Storage

Important Note:

WACKER® PRIMER G 719 is sensitive towards humidity. In contact with moisture the liquid primer becomes turbid and the adhesive strength of the primer is impaired. WACKER® PRIMER G 719 should therefore be stored in a sealed container after usage. In addition, it is strongly recommended to stir or shake the primer thoroughly before applying.

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code WACKER® PRIMER G 719



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.